

I claim:

1. A method for retreading a tire comprising a carcass comprising the step of spraying on the radially outermost surface of the carcass rubber comprising a curing accelerator in a thermoplastic matrix.
2. The method of claim 1, wherein the matrix is selected from the group consisting of polymethylmethacrylate and polycarbonate.
3. The method of claim 1, wherein the accelerators are selected from the group consisting of zinc dibenzylthiocarbamate and diphenyl guanidine.

10